PITERNATIONAL PRELIMINARY EXAMINING AUTHORITY

To:

FRANK B. DEHN & CO. 179 Queen Victoria Street London EC4V 4EL **GRANDE BRETAGNE**

NOTIFICATION OF TRANSMITTAL OF THE INTERNATIONAL PRELIMINARY **EXAMINATION REPORT**

(PCT Rule 71.1)

2 2 SEP 2004

File

Frank B. Dehn & Co. RECEIVE of mailing

20.09,2004

Applicant's or agent's file reference

3.35.82770/001

IMPORTANT NOTIFICATION

International application No.

PCT/FI 03/00501

International filing date (day/month/year) 19.06.2003

Priority date (day/month/year)

24.06.2002

Applicant

BOREALIS TECHNOLOGY OY

- 1. The applicant is hereby notified that this International Preliminary Examining Authority transmits herewith the international preliminary examination report and its annexes, if any, established on the international application.
- A copy of the report and its annexes, if any, is being transmitted to the International Bureau for communication to all the elected Offices.
- Where required by any of the elected Offices, the International Bureau will prepare an English translation of the report (but not of any annexes) and will transmit such translation to those Offices.

4. REMINDER

The applicant must enter the national phase before each elected Office by performing certain acts (filing translations and paying national fees) within 30 months from the priority date (or later in some Offices) (Article 39(1)) (see also the reminder sent by the International Bureau with Form PCT/IB/301).

Where a translation of the international application must be furnished to an elected Office, that translation must contain a translation of any annexes to the international preliminary examination report. It is the applicant's responsibility to prepare and furnish such translation directly to each elected Office concerned.

For further details on the applicable time limits and requirements of the elected Offices, see Volume II of the PCT Applicant's Guide.

The applicant's attention is drawn to Article 33(5), which provides that the criteria of novelty, inventive step and industrial applicability described in Article 33(2) to (4) merely serve the purposes of international preliminary examination and that "any Contracting State may apply additional or different criteria for the purposes of deciding whether, in that State. the claimed inventions is patentable or not" (see also Article 27(5)). Such additional criteria may relate, for example, to exemptions from patentability, requirements for enabling disclosure, clarity and support for the claims.

Name and mailing address of the international preliminary examining authority:

European Patent Office - P.B. 5818 Patentlaan 2 NL-2280 HV Rijswijk - Pays Bas Tel. +31 70 340 - 2040 Tx: 31 651 epo nl Fax: +31 70 340 - 3016

Authorized Officer

Dekker, M

Tel. +31 70 340-4046





PATENT COOPERATION REATY

PCT

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference 3.35.82770/001		FOR FURTHER ACTIO	FOR FURTHER ACTION See Notification of Transmittal of Internation Preliminary Examination Report (Form PC)				
		International filing date (day/m	onth/year)	Priority date (day/month/year)			
		19.06.2003		24.06.2002			
Internation C08L23/	06	or both national classification and IP	C				
Applicant BOREAL	LIS TECHNOLOGY OY						
1. This	s international preliminary e nority and is transmitted to	xamination report has been pre the applicant according to Articl	pared by this e 36.	International Preliminary Examining			
 This REPORT consists of a total of 6 sheets, including this cover sheet. 							
⊠	been amended and are t	panied by ANNEXES, i.e. shee he basis for this report and/or sh tion 607 of the Administrative In	eets containi	ription, claims and/or drawings which have ng rectifications made before this Authority der the PCT).			
The	se annexes consist of a to	al of 5 sheets.					
3. This	report contains indications	s relating to the following items:					
1							
II	☐ Priority	·					
Ш	☐ Non-establishment	Non-establishment of opinion with regard to novelty, inventive step and industrial applicability					
IV	☐ Lack of unity of inve						
٧		Reasoned statement under Rule 66.2(a)(ii) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement					
VI	☐ Certain documents	cited					
VII	☐ Certain defects in t	ne international application					
VIII	☐ Certain observation	s on the international applicatio	n				
Date of sul	omission of the demand	Date	of completion	of this report			
09.01.2004		20.	20.09.2004				
	mailing address of the interna	tional Auth	orized Officer	disches Palonzony.			
European Patent Office - P.B. 5818 Patentlaan 2 NL-2280 HV Rijswijk - Pays Bas Tel. +31 70 340 - 2040 Tx: 31 651 epo nl Fax: +31 70 340 - 3016			ımidt, H	on the contract of the contrac			
			phone No. +31	70 340-2461			

IN ERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/FI 03/00501

l. Basis	of the	report
----------	--------	--------

1. With regard to the **elements** of the international application (Replacement sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to this report since they do not contain amendments (Rules 70.16 and 70.17)):

	Des	scription, Pages						
	1-1	8, 20, 21	as originally filed					
	19		received on 13.08.2004 with letter of 11.08.2004					
	Cla	ims, Numbers						
	1-2	0	received on 13.08.2004 with letter of 11.08.2004					
2.	With lang	h regard to the langu guage in which the int	age, all the elements marked above were available or furnished to this Authority in the ernational application was filed, unless otherwise indicated under this item.					
	The	nese elements were available or furnished to this Authority in the following language: , which is:						
		the language of a tra	unslation furnished for the purposes of the international search (under Rule 23.1(b)).					
			ication of the international application (under Rule 48.3(b)).					
		the language of a translation furnished for the purposes of international preliminary examination (under Rule 55.2 and/or 55.3).						
3.	Witl inte	With regard to any nucleotide and/or amino acid sequence disclosed in the international application, the international preliminary examination was carried out on the basis of the sequence listing:						
		contained in the inte	rnational application in written form.					
		filed together with th	e international application in computer readable form.					
		furnished subsequer	ntly to this Authority in written form.					
		furnished subsequer	ntly to this Authority in computer readable form.					
		The statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.						
		The statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished.						
4.	The	amendments have r	esulted in the cancellation of:					
		the description,	pages:					
		the claims,	Nos.:					
		the drawings,	sheets:					
5.		This report has been been considered to	established as if (some of) the amendments had not been made, since they have go beyond the disclosure as filed (Rule 70.2(c)).					
		(Any replacement st report.)	neet containing such amendments must be referred to under item 1 and annexed to this					
3.	Αdd	litional observations	if necessary					

In PERNATIONAL PRELIMINARY **EXAMINATION REPORT**

International application No.

PCT/FI 03/00501

V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement

1. Statement

Novelty (N)

Yes: Claims

1-20

No:

Inventive step (IS)

Claims Yes: Claims

No: Claims 1-20

Industrial applicability (IA)

Yes: Claims

1-20

No: Claims

2. Citations and explanations

see separate sheet

EXAMINATION REPORT - SEPARATE SHEET

Box I

1. The following documents (D1-D2) are referred to in this opinion: the numbering will be adhered to in the rest of the procedure:

D1 US-A-6096014

D2 WO-A-9941310

Box VIII

- 2. The application does not meet the requirements of Article 6 PCT, because claims 1, 7, 14 and 15 are not clear.
- 2.1 Present claims 1, 7 and 14 specify ranges for the properties melt flow rate and density of polymer (ii). Polymer (iii) has a lower melt index and a density than polymer (ii). The terms "lower" and "higher" are unclear: a skilled man does not know, which difference between the values of (ii) and (iii) are necessary (i.e. a difference in density of 0.0001 g/cm3 or 0.1 g/cm3 etc.) to obtain the desired technical effects, if any, and solve the technical problem.
- 2.2 The MFR2, MFR21 and density values of the bimodal ethylene composition are unclear in claim 1 and 7. As long as the term "comprising" is used under (i), these values are not only depending on the properties of (ii) and (iii), but also on the other components of (i). There is hence no clear definition for the properties of (i) and (iii). A skilled man reproducing the invention does not know how to obtain these values and how to choose (i) and (iii)
- 2.4 The value of the water vapour transmission is dependant on parameters not indicated in the claim like thickness of the film and additional additives. The disclosure of the apparatus used for the measurement alone is not sufficient for clarifying claim 15

Box V

3. The present claims appear to be novel acc. Art. 33(2) PCT.

D1 discloses microporous breathable films of CaCO₃ and blends of ethylene polymers with different melt indexes and densities. None of the resins disclosed has a melt flow rate of 50-500 g/10 min

D2 discloses non-breathable films of blends comprising 40% polyethylene of density=.97 g/cm³, MI 410 g/10 min. The final composition has a density of d=.930 g/cm³ and MFR₂₁=20 g/10 min. These parameters correspond to the present (i-a) and (i-b). D2 does not disclose additives

- 4. The present application does not meet the requirements of Article 33(3) PCT, because the subject-matter of claims 1-20 does not involve an inventive step
- 3.1 Subject matter of claim 1 is a compositions of
- (i) 20-50% bimodal polyethylene composition of
 - (ii) 37-48% low molecular weight of a melt flow rate of 50-500 g/10min and a density of .94-.975 g/cm³
 - (iii) 52-63% a polyethylene of higher molecular weight (lower melt flow rate) and lower density
- (iv) 40-70% particulate filler

Subject matter of claim 7 is a corresponding breathable film, subject matter of claim 14 a process of preparing such a film

3.2 Closest prior art is D1 disclosing a microporous breathable films of CaCO₃ and a blend of ethylene polymers with melt flow and density properties different from present claim 1.

The working examples of the present application are based on bimodal polymer composition (2)-(4), of which only (2)-(3) is according the invention (the MFR₂ of the entire bimodal polymer (4) is not determined). All the examples lead to breathable films (examples 5-10) using different compositional ranges of bimodal polymers. Since threre are no comparative examples, there is no evidence of advantageous technical effects. The problem to be solved by the present claims hence is to provide alternative compositions for breathable films with good mechanical properties, the corresponding breathable films and processes.

The use of bimodal compositions fullfilling the parameters of the present claims for films in general is known from D2, example 1. The choice of just another parameter range cannot be regarded as a solution giving rise to an inventive step. As long as there is no evidence for a technical effect generated by the use of the compositions of D2 in the breathable films of D1, the present claim only makes a choice out of equally likely alternatives. Such a choice is obvious and non-inventive.

D2 is disclosing compositions for films. These compositions have the same properties

INTERNATIONAL PRELIMINARY International application No. PCT/FI 03/00501 XAMINATION REPORT - SEPARATE SHEET

as the bimodal compositions claimed in claim 1. A skilled man knows that breathability is a result of adding filler particles and subsequently stretching. All compositions suitable for films hence are also suitable for breathable films if the corresponding filler is added. A skilled man hence would consult D2 as well as all other documents relating to films if he wants to modify D1. In the present case, it is not the question in how many parameters D1 is differing from present claim 1, but whether the film foming polymer composition of D1 can be replaced by another - the one of D2. For a skilled man it is no question that both composition are useful for films and that both are suitable for breathable films, if a corresponding additive is added.







Table 1: Production data of Examples 2,3 and 3

Example	2	3	4
Ethylene concentration in loop reactor, mol-%		6.7	6.7
Hydrogen to ethylene ratio in loop reactor,		265	305
mol/kmol			
1-butene to ethylene mole ratio in loop reactor,	570	514	0
mol/kmol			
Polymer production rate in loop reactor, kg/h	25	26	25
MFR ₂ of polymer produced in loop reactor, g/10	300	300	300
min			
Density of polymer produced in loop reactor,	951	951	975
kg/m ³			
Ethylene concentration in gas phase reactor, mol-	19	7.8	8.2
%			
Hydrogen to ethylene ratio in gas phase reactor,		7	8
mol/kmol			
1-butene to ethylene mole ratio in gas phase		460	480
reactor, mol/kmol			
Average particle size of the powder, mm		0.36	ND
MFR ₂ of the final polymer, g/10 min		0.21	ND
MFR ₂₁ of the final polymer, g/10 min		22	20
Density of the final polymer, kg/m ³		923	931
Split, loop/gpr		41/59	41/59

ND denotes that the respective property has not been determined

Example 6

The procedure of Example 5 was repeated, except that the polymer composition comprised of 40 % by weight of polymer produced in Example 2 as the bimodal polyethylene composition and 60 % by weight of CaCO₃. The composition was then blown to a film and the resulting film was stretched in the machine direction 6 times its original length. The resulting film had a thickness of 19 μm, a basis weight of 16 g/m², tensile strength in the machine direction of 59 MPa, and in the transverse direction of 4.1 MPa. Tear strength in






15

20





DT12 Rec'd PCT/PTO 0 9 DEC 2004

- 22 -

82770/001.624

Claims

- 1. A composition for making breathable films, the composition comprising:
- 5 (1) 20-50%, based on the weight of the total composition, a bimodal polyethylene composition, further comprising
 - a first low molecular weight component, which is a homopolymer of (i-a) ethylene or a copolymer of ethylene and one or more C₄ to C₁₀ alpha-olefins, having a melt flow rate, determined according to ISO 1133 at 190°C, MFR2 of 50 to 500 g/10 min, preferably of 100 to 400 g/10 min and a density of 940 to 975 kg/m³, preferably 945 to 975 kg/m³, the first component being present in the bimodal polyethylene composition in an amount of 37 to 48% by weight. (i-b) at least a second component, which is a copolymer of ethylene and one or more C₄ to C₁₀ alpha-olefins, having a higher molecular weight, a lower melt flow rate and a lower density than the said first component, the second component being present in the bimodal polyethylene composition in an amount of 52 to 63% by weight, so that the said bimodal polyethylene composition has a melt flow rate, determined according to ISO 1133 at 190°C. MFR₂ in the range of 0.1 to 4.0 g/10 min, MFR₂₁ in the range of 15 to 200 g/10 min, and a density of 918 to 935 kg/m³,
 - (ii) 40-70%, based on the weight of the total composition, a particulate filler, and
 - (iii) 0-30%, based on the weight of the total composition, another olefin-based polymer.
- 25 2. The composition according to Claim 1, wherein the other olefin based polymer is selected from the group of homo- and copolymers propylene, 1-butene and 4-methyl-1-pentene.
- The composition according to Claim 1 or 2, wherein the other olefin based
 polymer is a propylene homo- or copolymer, preferably a copolymer of propylene and ethylene.











- 23 -

- 4. The composition according to Claim 3, wherein the composition comprises of 5 to 20%, based on the weight of the total composition, of the said propylene polymer.
- 5 5. The composition according to Claim 1, wherein the content of the particulate filler is 55 to 70%.
 - 6. A composition according to any one of the preceding claims, wherein the particulate filler is calcium carbonate.

10

- 7. The composition according to claim 1 wherein said bimodal polyethylene composition has the following properties (a) to (d):
 - (a) density from 918 to 935 kg/m³
 - (b) melt flow rate MFR₂ from 0.1 to 0.8 g/10 min;
- 15 (c) melt flow rate, determined according to ISO 1133 at 190°C, MFR₂₁ from 15 to 70 g/10 min;
 - (d) flow rate ratio MFR₂₁/MFR₂ from 60 to 120.
- 8. The composition according to Claim 7, wherein the bimodal polyethylene composition has:
 - (e) a weight average molecular weight (Mw) from 150000 to 300000 g/mol;
 - (f) a ratio of the weight average molecular weight to the number average molecular weight (M_w/M_n) from 7 to 30; and
 - (g) a content of alpha-olefin comonomer units of 2 to 5% by mole.
 - 9. The composition according to any one of Claims 7 or 8, wherein the other olefin based polymer is a propylene homo- or copolymer, preferably a copolymer of propylene and ethylene.

30

25

10. The composition according to Claim 9, wherein the composition comprises of 5 to 20%, based on the weight of the total composition, of the said propylene







- 24 -

polymer.

- 11. The composition according to any one of Claims 7 or 8, wherein the content of the particulate filler is 55 to 70%.
- 12. A composition according to any one of Claims 7 to 11, wherein the particulate filler is calcium carbonate.
- 13. The use of the composition according to any one of Claims 1 to 12 for10 making films.
 - 14. A breathable polymer film, which film comprises a composition according to any one of Claims 1 to 12.
- 15. A film according to Claim 14 wherein the film has a water vapour transmission rate, measured using a Permatran W100K water vapour permeation analysis system, of more than 3000 g/m²/24 h, preferably more than 4000 g/m²/24 h.
- 16. A film according to any one of Claims 14 to 15, wherein the film has a basis weight of less than 25 g/m².
 - 17. A process for producing a breathable polymer film, comprising the steps of:
 - (A) providing into an extruder a composition according to any one of Claims 1 to 12
- 25 (B) extruding the composition to a film
 - (C) stretching the film to produce a breathable film.
 - 18. The process according to Claim 17, wherein the film is stretched with a stretching ratio of 3 to 10, preferably 4 to 7.
 - 19. The process according to any one of Claims 17 to 18, wherein the bimodal polyethylene composition has been produced by a process comprising the steps of:

30

10

15

20





- 25 -

- (i) subjecting ethylene, hydrogen and optionally comonomers to a first polymerisation or copolymerisation reaction in the presence of the polymerisation catalyst in a first reaction zone or reactor to produce a first polymerisation product having a low molecular weight with a melt flow rate, determined according to ISO 1133 at 190°C, MFR₂ of 50 to 500 g/10 min, preferably of 100 to 400 g/10 min and a density of 940 to 975 kg/m³, preferably 945 to 975 kg/m³,
- (ii) recovering the first polymerisation product from the first reaction zone,
- (iii) feeding the first polymensation product into a second reaction zone or reactor,
- (iv) feeding additional ethylene, comonomers and optionally hydrogen to the second reaction zone,
- subjecting additional ethylene and additional comonomer(s) and optionally hydrogen to the second reaction zone in the presence of the said polymerisation catalyst and the first polymerisation product,
- (vi) to produce a polymer composition comprising from 41 to 48% by weight of the low molecular weight polymer produced in step (i), and from 59 to 52% by weight of the high molecular weight component produced in step (v),
- (vii) the composition having a melt flow rate, determined according to ISO 1133 at 190°C, in the range MFR₂ of 0.1 to 4.0 g/10 min, preferably 0.1 to 0.8 g/10 min and a density of 918 to 935 kg/m³, and
 - (viii) recovering the combined polymerisation product from the second reaction zone.
- 25 20. The process according to Claim 19, wherein at least part of the volatile components of the reaction medium are evaporated and removed from the first polymerisation product before the said first polymerisation product is introduced into the second reaction zone or reactor.